



Technical Data Sheet
Revised: 02/2020

Fiber: 100% SaturaMax Polyester w/ ultra-high UV resistance
100% Pigment solution-dyed
Finish: DWR and Coating (underside) + FR
Width: 60" fused edge
Put Up: 65 yards

Meets Fire Codes: CSFM Title 19 / CPAI-84 / NFPA 701 / FMVSS 302
ASTM E84 Class A & Class 1 / German B1 / FAR 25.853

Test	Method	Basis	Nominal Value
Fabric Weight	ASTM D3776	Ounces / Square Yard	9.75
Finished Fabric Width	ASTM D3774	Inches	60.0
Hydrostatic Test	AATCC 127	cm.	90+
Oil Repellency	AATCC 118	Grade	5-6
Spray (Large)	AATCC 22	Rating	100
Air Perm	ASTM D 737	CFM	0.2
Break Strength	ASTM D5034	lbs.	410 Warp 340 Fill
Tear Strength	ASTM D2261	lbs.	12 Warp 14 Fill
Wyzenbeek Abrasion - Wire Screen	ASTM D4157	Cycle	50,000+ Warp 50,000+ Filling
Colorfastness to Light	SAE 1960J	Grade	Grade 4-5 @ 1500 hrs
UVA & UVB		Ultraviolet blockage	Over 99%

Other test results available upon request

elevate Textiles™

